



355 Hollow Hill Drive
Wauconda, IL 60084
Ph: 847.487.4583
Fax: 847.487.0174
E-mail: glueguns@aol.com
www.surebonder.com

Specification Sheet 930

Type: Hot Melt Adhesive

Viscosity ¹: 2000 cps @ 375°(F)

Open Time: Up to 7 minutes(bead), up to 3 minutes(spray)

R & B Softening Point: 190° (F)

Color: Off-white

Odor: Slight

Shelf Life: Indefinite

Flash Point: Above 450° (F)

FDA Status: Compositional compliance with FDA Regulation #21CFR175.105 for food packaging.

Application Temperature: 350° (F) to 390° (F)

Common Applications: Long open time hot melt for difficult to bond substrates. Bonds to a variety of foams, plastics, metal, wood, vinyl, glass and ceramics.

Precautions: Do Not Mix with other adhesives.
Severe burns will result if contact is made in molten state.
Material safety data sheets provide safety precautions that should be observed in handling and storing.

The buyer should conduct its own tests of this product before use to determine proper preparation, technique and suitability for proposed application. FPC warrants that the product conforms with FPC written specifications, and is free from defects. FPC disclaims all other warranties, expressed or implied, including the warranties of merchantability and fitness for a particular purpose. The buyer's sole remedy for non compliance with this warranty shall be for the replacement of the product or refund of the buyer's purchase price.

AVAILABLE SIZES:

930R10 - 7/16" x 10" sticks
Q-930-15 - 5/8" x 15" sticks